

REPELLANT RENDER RR60

PRODUCT DESCRIPTION

DMC RR60 is a premixed sprayable grey render with highly water repellent properties for the application of below and near ground level rendering. It can be used on all interior and exterior surfaces with minimum preparation of the wall. It is formulated to resist weather and the effects of salt water contamination at ground level. RR60 combines easy workability with crack-free curing. RR60 is developed for the harsh Middle East climate conditions and optimized for the latest automatic conveying, mixing and spraying machines. RR60 is ideal in combination with all DMC finishing products.

TYPICAL APPLICATIONS

DMC RR60 is a premixed sprayable grey render with highly water repellant properties for the application of below and near ground level rendering.

FEATURES & BENEFITS

- No dash coat needed on any blocks and bricks
- Spray application for maximum m² per day
- Easy workability for fast work progress

APPLICATION PROCEDURE

Surface preparation:

All surfaces must be clean, sound and free from all traces of oil, grease, mold release agent and curing compound. Concrete, renders and blockwork should be cured sufficiently that all shrinkage has occurred. Fair-faced concrete or other smooth low absorbent substrates should be prepared with DMC Bridge BB60. Larger surface inconsistencies should be filled and leveled out with RR60 in advance.

Mixing instructions:

Add 25KG of RR60 to 7.0L of cool, clean and salt-free water. Mix to a uniform lump free consistency ideally with a mixing machine at slow speed. DMC recommends to use RR60 with an automatic mixing and spraying machine to enhance mixing quality and increase productivity.

Application instructions:

Dampen substrate with clean and salt-free water directly before application. Apply thick layer of material with trowel or spray gun to the wall. Don't exceed maximum thickness per layer of 25mm. If required thickness exceeds 25mm apply material in several layers. Distribute and level applied material with aluminum profile within maximum 10 minutes after application. Wait until material starts setting properly. Then open surface by scratching with rabbot to enable release of residual moisture. Wait for 30 minutes before finishing the surface with sponge float to create desired design.

All data is derived by approved testing methods and application experiments under laboratory conditions Deviations are possible under practical conditions.

TECHNICAL DATA

COMPOSITION

Binder:

Grey cement Hydrated lime Graded sand

Aggregates:

Additives:

(max. grain size 1.6mm) Organic polymers to improve consistency and

workability

SUBSTRATES

AAC (inside only), blockwork, red brick

APPLICATION

Mixing ratio: Max. thickness/layer 7.0L per 25KG 25mm

TYPICAL PROPERTIES

Appearance: Bonding strength:

Colour:

Compressive strength: Consumption per m²: Flexural strength:

Min. first layer thickness: Mortar class: Yield: approx.

Light grey powder

 $> 0.1 N/mm^2$ Grev

> 8N/mm² 1.29kg/mm $> 3.5 N/mm^2$

15_{mm} CS IV 775L/Ton

FIRE CLASSIFICATION

A1, 100% noncombustible (EN 13501-1)



REPELLANT RENDER RR60

APPLICATION PROCEDURE CONTINUED

Curing:

Please refer to Method Statement for curing details.

APPLICATION TEMPERATURE

Do not use material below 5°C, schedule work for morning hours during extreme heat.

LIMITATIONS OF USAGE

- Avoid applying the material in direct sunlight
- Always add material to the water
- Do not re-temper mixed material
- Do not mix with any other material
- Setting time of the product may vary largely depending on climatic conditions, substrates and application thickness of the product

TECHNICAL INFORMATION

Consult the DMC Technical Services Department for specific recommendations concerning all other applications.

Visit the DMC website www.dmc-mix.com for additional information about products, systems and for updated literature.

SAFETY PRECAUTIONS

As with all building products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs.

Treat splashes to eye and skin immediately. If accidentally ingested, seek immediate medical attention. Use in well ventilated areas. Avoid inhalation of dust when using powdery products.

Wear suitable protective gloves, safety goggles and respiratory protection mask.

STORAGE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. Shelf life is 9 months for all dry mortar products and 3 months for all liquids.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult DMC's Technical Services Department.

PACKAGING

- 25KG bag
- 1,200KG jumbo bag
- Silo (check availability in your area)



NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local DMC representative.

DMC reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY & CARE

All products originating from DMC Saudi Arabia are manufactured under conformity to the requirements of the quality, environmental and occupational health & safety standards of the above mentioned SASO, ANSI, ASTM, ISO and DIN EN norms.

DISCLAIMER

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labor involved in the application are beyond our control.

All data is derived by approved testing methods and application experiments under laboratory conditions. Deviations are possible under practical conditions. As all DMC technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

Dry Mortar Company P.O. Box 355 798 Riyadh 11383 Kingdom of Saudi Arabia Tel: (011) 210 97 58 Fax: (011) 275 47 93 info@dmc-mix.com www.dmc-mix.com